

# **Confidential Report**

Our Ref: 27/04626/05/18



Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339



Telephone: +44 (0) 113 259 1999 Email: info@bttg.co.uk

Website: www.bttg.co.uk

24 May 2018 Date:

27/04626/05/18 Our Ref:

Your Ref:

Page: 1 of 7

| Client: | Igloo Surfaces Limited                 |
|---------|--|
|         | Unit 12C, Goldthorpe Industrial Estate |

Rotherham S63 9BL

Job Title: Fire Test on One Sample of PVC Sheeting

Client's Order No:

Date of Receipt: 18 May 2018

One sample of PVC sheeting adhered to plasterboard. The sample was labelled as: Description of Sample(s):

> Arctic PVC Sheet having a thickness of 2.5mm and a weight of 3.65kg/m<sup>2</sup>, bonded with Igloo polyurethane adhesive at an application rate of 2kg/m<sup>2</sup> to a 12mm thick

gyproc plasterboard.

Work Requested: We were asked to make the following test(s):

BS 476 Part 6 & 7

Note: This report relates only to the samples submitted and as described in the report.

- subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 2 of 7

Client: Igloo Surfaces Limited

## FIRE TESTS ACCORDING TO BS 476:PART 7:1987 (AS AMENDED) (Method for classification of the surface spread of flame of products)

Date of Test: 23/05/2018

## **Conditioning**

The sample was conditioned to constant mass at a temperature of 23±2°C and a relative humidity of 50±10% and maintained in this condition until required for testing

#### **Procedure**

The test was carried out in accordance with BS 476:Part 7: 1987. The sponsor sampled the material and the specimen was cut from the sample to the dimensions set out in the standard by FTS. The specimens were tested as received.

The following were recorded:-

- a) the time at which the flame front crosses each vertical reference line;
- b) the maximum extent of flame spread during the first 1.5 min from the start of the test;
- c) the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- d) the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 3 of 7

**Client: Igloo Surfaces Limited** 

## Requirements

The class limits for flame spread, detailed in BS 476:Part 7: are set out below.

|         | Flame spread at 1.5 min (mm) | Final flame spread (mm) |  |  |  |
|---------|------------------------------|-------------------------|--|--|--|
| Class 1 | 165 (+25)                    | 165 (+25)               |  |  |  |
| Class 2 | 215 (+25)                    | 455 (+45)               |  |  |  |
| Class 3 | 265 (+25)                    | 710 (+75)               |  |  |  |
| Class 4 | Exceeding Class 3 limits.    |                         |  |  |  |

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

### **Results**

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

| Time for flame<br>spread to reach (s)<br>(mm) |     |     |     |     | Flame spread at 1.5 min | Maximum flame spread | Time to reach<br>maximum<br>flame spread |      |      |     |
|---|-----|-----|-----|-----|-------------------------|----------------------|--|------|------|-----|
| 75  | 165 | 215 | 265 | 455 | 710                     | 785                  | 825                                      | (mm) | (mm) | (s) |
|   |     |     |     |     |                         |                      |  | 60   | 60   | 61  |
|   |     |     | 1   |     |                         | -                    |  | 60   | 60   | 61  |
|   |     |     | 1   |     |                         | 1                    |  | 60   | 60   | 61  |
|   |     |     |     |     |                         |                      |  | 60   | 60   | 61  |
|   |     |     |     |     |                         |                      |  | 60   | 60   | 61  |
|   |     |     |     |     |                         | -                    |  | 60   | 60   | 61  |

The results indicate that the sample met the performance requirements of Class 1.

## **Observations**

Specimens 1, 2 and 4 reignited above the reference line.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 4 of 7

Client: Igloo Surfaces Limited

## FIRE TESTS ACCORDING TO BS 476-6:1989+A1:2009 (2015)

Fire tests on building materials and structures. Method of test for fire propagation for products

Date of Test: 23/05/2018

#### **Test Method**

The test was carried out in accordance with BS 476-6:1989+A1:2009 (2015).

Prior to testing the sample the calibration of the equipment was determined to ensure compliance with the test limits set out in the standard.

The sponsor sampled the material and the specimen was cut from the sample to the dimensions set out in the standard by FTS. The specimens were tested as received.

Temperatures of the flue gases were measured to the nearest degree centigrade at the time intervals and periods set out below, taking zero time as the moment of ignition of the gas supply. The temperature was measured by means of two thermocouples with their measuring junctions located in the cowl of the apparatus as required by the standard.

The relevant temperature-time intervals were observed for each individual specimen and the calibration board according to the ranges 0 to 3 minutes every 30 seconds, 4 to 10 minutes every 1 minute and 12 to 20 minutes every 2 minutes to give 3 time periods.

N.B: The shrinkage in the plane of the calibration board was not determined after heat soaking at 1000°C.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 5 of 7

Client: Igloo Surfaces Limited

### **Calculation of Results**

At each time interval the temperature of the calibration board was subtracted from that of the individual specimen temperature, this was then divided by ten multiplied by the time interval.

The sum of each individual value in each time period was then calculated to give an index of performance, s, for each specimen.

The fire propagation index of the product is calculated from the average of the individual s values for the total number of specimens in each time period.

Total I =  $i_1 + i_2 + i_3$ 

A definitive classification is based on a sample of at least three specimens.

## Requirements

A Class 0 is the highest National product performance classification for lining materials. To meet Class 0 a material has to meet the requirements laid down in the UK Building Regulations 2010, Approved Document B, Appendix A that states that a composite material is either:

- a) composed throughout of materials of limited combustibility; or
- b) a class 1 material which has a propagation index (I) of not more than 12 and a sub index (i<sub>1</sub>) of not more than 6 when tested to BS 476 Part 6.

#### **Results**

| Number of specimens tested | Sub-index<br>i <sub>1</sub> | Sub-index<br>i <sub>2</sub> | Sub-index<br>i <sub>3</sub> | Total Fire propagation index |
|----------------------------|-----------------------------|-----------------------------|-----------------------------|------------------------------|
| 3                          | 0.1                         | 5.0                         | 3.7                         | 8.7                          |





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 6 of 7

**Client: Igloo Surfaces Limited** 

## **Comments**

In our opinion:-

- 1) The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.
- 2) The results indicate the sample meets the requirements of Class 0 of the UK Building Regulations 2010, Approved Document B, Appendix A.

| Reported by: | ciro CL | B Marsden (Mr | s), Fire T | echnician |
|--------------|---------|---------------|------------|-----------|
|--------------|---------|---------------|------------|-----------|

Countersigned by: P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services..





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 24 May 2018

Our Ref: 27/04626/05/18

Your Ref:

Page: 7 of 7

Client: Igloo Surfaces Limited

## **Uncertainty Budget - Annex**

The overall uncertainty budgets for BS 476-7:1987 and BS 476-6:1989+A1:2009 (2015) are as follows:-

BS 476-7:1987

Overall: ±20%

BS 476-6:1989+A1:2009 (2015)

Overall: ±6%

